

SIL 30

SIL 30 is a soft, biocompatible, and tear-resistant silicone urethane elastomer that is ideal for comfortable skin-contact applications.



www.qd-p.com

Carbon[®]

QDP
Geograaf 22
6921 EW Duiven
The Netherlands

+31 (0) 85 047 6600
info@qd-p.com
www.qd-p.com

Tensile Properties ASTM D412, Die-C Shape, 500 mm/min	Metric	U.S.
Ultimate Tensile Strength	3.2 MPa	460 psi
Elongation at Break	> 330 %	
Stress at 50 % Elongation	0.42 MPa	61 psi
Stress at 100 % Elongation	0.69 MPa	100 psi
Stress at 200 % Elongation	1.45 MPa	210 psi
Mechanical Properties	Metric	U.S.
Tear Strength, ASTM D624, Die-C (die cut)	9.6 kN/m	55 lb _f /in
Compression Set, 23 °C, 72 hrs, ASTM D395-B	11 %	
Bayshore Rebound Resilience, ASTM D2632	20 %	
Thermal Properties	Metric	U.S.
T _g (DMA, tan(d)), ASTM D4065	8 °C	46 °F
Dielectric Properties ASTM D150, 1 MHz	Metric	
Dissipation Factor	0.15	
Dielectric Constant	7.6	
General Properties	Metric	
Hardness, Shore A, ASTM D2240	35 (instant), 31 (5 sec)	
Density, ASTM D792	1.07 g/cm ³	
Density (liquid resin)	1.05 g/cm ³	

NOTES—Results in this data sheet represent typical values from specific sample generation and testing processes and may vary if the established protocols are not followed. Contact Carbon for the specific process used to generate the test samples to determine each of these values. The U.S. values are converted from Metric measurements and are for reference only.

The information in this document includes typical values from printing various parts and is intended for reference and comparison purposes only. This information should not be used for testing, design specification or quality control purposes. End-use material performance can be impacted by, but not limited to, design, processing, operating and end-use conditions, test conditions, color, etc. Actual values will vary with build conditions. In addition, product specifications are subject to change without notice.

This information and Carbon's technical advice are given to you in good faith but without warranty. The application, use and processing of these and other Carbon products by you are beyond Carbon's control and, therefore, entirely your own responsibility. Carbon products are only to be used by you subject to the terms of the written agreement by and between you and Carbon.

You are responsible for determining that the Carbon material is safe, lawful, and technically suitable for the intended application, as well as for identifying the proper disposal (or recycling) method consistent with applicable environmental laws and regulations. CARBON MAKES NO WARRANTIES OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR USE, OR NON-INFRINGEMENT. Further, it is expressly understood and agreed that you assume and hereby expressly release Carbon from all liability, in tort, contract or otherwise, incurred in connection with the use of Carbon products, technical assistance and information. Any statement or recommendation not contained herein is unauthorized and shall not bind Carbon. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.



**We create.
We produce.**

QDP

Geograaf 22
6921 EW Duiven
The Netherlands

+31 (0) 85 047 6600
info@qd-p.com
www.qd-p.com